

LOCTITE®



LOCTITE® HY 4090™ – Structural Hybrid Adhesive

Henkel's innovative technology delivers the strength of a structural adhesive with the speed of an instant adhesive

LOCTITE® HY 4090™ structural hybrid adhesive is an innovative hybrid technology that provides the bond strength and speed you need to solve your design and assembly challenges. With the strength of a structural adhesive and the speed of an instant adhesive, LOCTITE® HY 4090™ offers both performance and versatility.

This powerful combination provides impact resistance, high strength bonding on a variety of substrates, and excellent chemical resistance – making LOCTITE® HY 4090™ the essential adhesive solution. LOCTITE® HY 4090™ opens the door to new applications and new solutions.

These are just some of the benefits of LOCTITE® HY 4090™:

- Strength of a structural adhesive
- Speed of an instant adhesive
- Impact and vibration resistance
- Temperature resistance up to 300°F (150°C)
- Gap filling up to 0.2" (5 mm)
- Suitable for a variety of substrates, including metals, most plastics and rubbers

Now available
in 400g package
size for larger
applications



Nozzles sold separately.

na.henkel-adhesives.com/4090





LOCTITE® HY 4090™ STRUCTURAL HYBRID ADHESIVE

delivers high quality performance in extreme environments and challenging conditions. This hybrid powerhouse provides the necessary versatility to solve most every design, assembly and repair challenge.

In addition to combining the critical attributes of structural and instant adhesives, LOCTITE® HY 4090™ offers:

- Fast fixture times even at low temperatures 40°F (5°C)
- Low blooming
- Good UV resistance
- Optimized packaging and longer open times for larger surface applications



Features and Benefits:

 <p>Speed for applications that require the speed of an instant adhesive</p>	 <p>Impact Resistance for highly stressed joints and applications exposed to vibrations</p>	 <p>High Moisture Resistance for applications that demand good humidity and solvent resistance in various environments</p>	 <p>300°F (150°C) Up to 300°F (150°C) Temperature Resistance tested to resist even extreme heat conditions</p>	 <p>Gap Filling up to 0.2" (5 mm) for fast bonding of structural parts; fills gaps within 3-5 min. open time</p>
---	--	---	--	---

TECHNICAL DATA	
COLOR	Slightly cloudy to light yellow
APPEARANCE	High viscosity gel
MIX RATIO (VOLUME)	1:1
WORKING TIME	3 to 5 min.

PROPERTIES OF CURED MATERIAL		
LAP SHEAR STRENGTH, ISO 4587, AFTER 24 HOURS, 72°F (22°C)	Steel (grit blasted)	17 N/mm ²
	Aluminum (etched)	13 N/mm ²
	Polycarbonate	6.9 N/mm ²
HIGH GAP FILL	Up to 0.2" (5 mm) depending on bond geometry	
TEMPERATURE RESISTANCE	-40°F to 300°F (-40°C to 150°C)	
CHEMICAL RESISTANCE	Very good chemical/solvent resistance	

HENKEL CORPORATION
 Engineering Adhesives
 One Henkel Way
 Rocky Hill, Connecticut 06067
 Tel: 1.800.LOCTITE (562.8483)
 Tel: 860.571.5100
 Fax: 860.571.5465
na.henkel-adhesives.com/4090

All marks used are trademarks and/or registered trademarks of Henkel and its affiliates in the U.S. and elsewhere.
 ® = registered in the U.S. Patent and Trademark Office. © 2016 Henkel Corporation. All rights reserved. 15759/LT-6961 (10/16)

